



# Enviro HP1200 + 950TC + Drainage

APPLICATION METHOD STATEMENT

## Table of Contents

<b>Table of Contents</b>	<b>2</b>
<b>Introduction</b>	<b>3</b>
<b>General Information</b>	<b>4</b>
<b>Product Specification</b>	<b>5</b>
<b>Application Procedure</b>	<b>7</b>
<b>Basic Requirements</b>	<b>12</b>
<b>Quality Inspection &amp; Assurance</b>	<b>13</b>
<b>Contact Enviro systems</b>	<b>14</b>

## Introduction

The Enviro HP1200 system is a high-performance waterproofing membrane specifically designed for demanding external waterproofing applications.

Enviro HP1200 is a two-component, spray-applied, solvent-free, flexible polyurethane membrane composed of 100% solids. It is engineered to deliver superior elongation, high tensile strength, and exceptional tear resistance, along with outstanding abrasion resistance and long-term durability.

This membrane has been independently tested by the Commonwealth Scientific and Industrial Research Organisation (CSIRO) and meets all performance criteria outlined in AS 4654.1:2012 for external above-ground waterproofing.

The following sections provide comprehensive instructions for the preparation of substrates and the correct installation procedures for Enviro HP1200.

## General Information

This installation manual has been developed by Enviro systems Technologies to support the structured and consistent application of Enviro systems waterproofing systems, with the objective of ensuring optimal product performance and quality control.

The design and installation of waterproofing membranes must be executed in accordance with applicable Environmental Protection Authority (EPA) regulations and all relevant statutory and legislative requirements.

The procedures and parameters detailed herein are intended to serve as general application guidelines and should be interpreted as such. This document does not supersede operational protocols or contractual requirements. All over coat times within this document are based on the temperature being 25°C and 50% RH. Different temperature conditions can affect the curing times.

Enviro systems Technologies accepts no liability for any damage, failure, or deficiency resulting from improper handling, installation, or subsequent modification of the products by any third party.

This manual is the intellectual property of Enviro systems Technologies and is protected under applicable copyright laws. Unauthorized reproduction, distribution, or use of its contents is strictly prohibited.

## Product Specification

Component	Details
Substrate	<p>Enviro HP1200 can be applied over the following suitably prepared substrates:</p> <ul style="list-style-type: none"> <li>• Concrete</li> <li>• Blockwork (flush joints)</li> </ul>
Patching	<p><u>Enviro Epoxy B-NS</u></p> <ul style="list-style-type: none"> <li>• Solvent Free, Thixotropic skimming and priming epoxy.</li> <li>• Applied by trowel, skimming across the substrate.</li> </ul>
Primer	<p><u>Enviro Prime 789</u></p> <ul style="list-style-type: none"> <li>• Enviro Prime 789 is a one-part moisture curing, low viscosity polyurethane that provides high bond strengths when used as a primer for Enviro HP1200 on non-porous substrates such as PVC.</li> <li>• It is to be applied to the prepared substrate at a rate of 7-10m<sup>2</sup>/L.</li> </ul>

Flexible Sealant	<p><u>Enviro Flex FL / FC</u></p> <ul style="list-style-type: none"> <li>• General purpose polyurethane sealant recommended for use under waterproofing membranes.</li> <li>• 15mm x 15mm fillets applied as per AS4654.2.</li> </ul>
Waterproofing Membrane	<p><u>Enviro HP1200</u></p> <ul style="list-style-type: none"> <li>• High Performance, Solvent Free, Plural Component Sprayed Elastomer Waterproofing Membrane.</li> <li>• Applied at a rate of 1.6kg /m<sup>2</sup> to a minimum dry film thickness (DFT) of 1.5mm.</li> </ul>
UV Topcoat (Only where exposed to UV)	<p><u>Enviro 950TC</u></p> <ul style="list-style-type: none"> <li>• Two-component 100% solids Aliphatic Polyurethane, UV coating, designed using the latest generation polyurethane technologies.</li> <li>• Applied at a rate of 0.23L /m<sup>2</sup> per coat to a minimum dry film thickness (DFT) of 0.22mm. 2 coats required for a total DFT of 0.440mm.</li> </ul>
Drainage	<p><u>Enviro H Cell (horizontal) or Enviro V Drain (vertical)</u></p> <ul style="list-style-type: none"> <li>• High flow drainage for below grade and planter boxes.</li> </ul>



## Application Procedure

Application is to be done by accredited applicators only and strictly in accordance with the product data sheet. The appropriate product data sheets should be read and understood thoroughly before the application.

### SUBSTRATE PREPARATION

#### Concrete

- Ensure that the concrete substrate is free from contaminants. Optimum surface preparation includes, mechanical profiling, such as captive shot blast cleaning or vacuum grinding to achieve a concrete surface profile (CSP) of CSP2/CSP3.
- Moisture content < 4.5%.

### PATCHING

#### Epoxy B-NS

- Enviro Epoxy B-NS is supplied in pre-weighed packages, of Part A- 20 Litres and Part B- 10 Litres. It is essential that all the hardener (Part B) is added to the entire resin component (Part A) to ensure that the correct mixing proportions are maintained (3 to 1, A: B, by volume).
- Combined components should then be thoroughly mixed using a mechanical stirrer with a paddle attachment for a minimum 5 minutes.
- Once fully mixed, Enviro Epoxy B-NS should be immediately applied by squeegee, trowel, roller or brush, to the prepared substrate to ensure that all imperfections are filled sufficiently.
- Enviro Epoxy B-NS has a pot life of 40 minutes at 25°C and 50% RH, mixed product should not be used after this time.
- Enviro Epoxy B-NS can be over coated after a minimum of 6 hours, assuming 25°C and 50% RH.

## PRIMER COAT

### Enviro Prime 789

- Enviro Prime 789 is a 1 component product.
- Apply by squeegee, roller or brush, to the prepared substrate. It should then be back rolled, with a medium nap roller to fill voids in the substrate.
- Enviro Prime 789 can be over coated after a minimum of 2 hours to 10 hours, assuming 10-15°C and 50% RH.

## ENVIRO HP1200 APPLICATION

### Mixing

- Enviro HP1200 is supplied in pre-weighed packages, of Part A- 23kg and Part B- 20kg. Mixing is by way of 1:1 mix ratio (by volume) in heated plural component spray equipment such as Graco E-10 or EXP-2.

### Application

- Enviro HP1200 application is to be by accredited / trained applicators only.
- Minimum application thickness is to be 1.5mm DFT.
- Application is to be by accredited applicators only and strictly in accordance with the technical data sheet
- HP1200 is to be finished to a taped day joint termination at the required thickness and not feather edged. All terminations, penetrations and joints are to be in accordance with EnviroSystems waterproofing details or project specific details (where provided).
- Do not apply Enviro HP1200, where:
  - Substrate temperature falls below 5°C, or exceeds 45°C
  - Rain is anticipated within 2 hours of application.

### Re-Coating

- Enviro HP1200 can be directly re-coated within <4 minutes and 3 hours of application, assuming 25°C and 50% RH.
- If 24 hours cure is allowed before re-coating (assuming 25°C and 50% RH), abrade the overlap section of Enviro HP1200 by mechanical means, solvent wipe with Enviro Thinners No1 and apply Enviro Shield over the HP1200 that is to be lapped to.

## ENVIRO 950TC APPLICATION

### Mixing

- Begin by pouring the Enviro 950 TC colour pack into Enviro 950 TC Part B. Mix for 3 minutes at 300 rpm. Then, add Part A to the mixture and continue mixing for another 3 minutes at 300 rpm. Allow the mixture to rest for 1 minute before use for optimal results.
- The pot life of Enviro 950TC is approximately 30 minutes at 25°C.

### Application

- Ensure the application of Enviro 950TC over Enviro HP1200 is within the overcoat window specified on the Enviro 950TC product data sheet (i.e. 10 minutes to 3 hours at 25°C and 55%RH). If this overcoat window is missed, the Enviro HP1200 is required to be solvent wiped and a coat of Enviro Prime P2 applied prior to Enviro 950TC application.
- Ensure the Enviro HP1200 surface to be coated with Enviro 950TC is free of all contaminants such as dust, grease, water etc.
- Use short nap (5-6 mm) mohair roller lint free. Do not apply in damp or wet conditions. Do not apply at low temperatures <5°C, as curing will be delayed. NOTE: Allow each coat to sufficiently dry before proceeding to the next coat. A thicker coat will take longer to dry.
- Shade the work area, and keep product stored in cool conditions out of direct sunlight. In cold weather, keep all products stored out of the cold, especially products not intended to be frozen. Warming materials to around 30°C can help but products may react to the substrate temperature rapidly when applied
- Apply each coat (2 coats required) at 0.23L/m<sup>2</sup> per coat to a DFT of 220 microns per coat.
- Refer to the below table for the minimum and maximum recoating of Enviro 950TC over Enviro 950TC.

Temperature	Minimum recoat	Maximum recoat
10°C @ 50%RH	4 hours	48 hours
15°C @ 50%RH	3 hours	24 hours
25°C @ 50%RH	2 hours	24 hours

If maximum recoat time between coats of 950TC is exceeded, abrade and reactivate with Enviro Thinner No. 1, apply Enviro Prime 789 then Enviro 950 TC topcoat.

## DRAINAGE APPLICATION

### Enviro H Cell drainage

- Position the cells: Lay Enviro H Cell drainage modules directly on top of the membrane. The modules interlock with each other to form a continuous drainage layer.
- Interlock & fit: Connect adjacent modules by interlocking edges or butting them together; cut modules as needed to suit edges or corners.
- Add protection: Cover the installed drainage layer with a layer of geotextile fabric to prevent soil ingress.
- Backfill: Spread a thin layer of coarse sand over the geotextile, then add planting soil and plants as required.

### Enviro V Drain

- Lay directly on waterproofing: Place the Enviro V Drain modular trays or dimple board directly over the finished waterproofing surface.  
Connect trays/sheets: Interlock adjacent trays/sheets to cover the entire area; trim to fit edges or corners where necessary.  
Secure and protect: Ensure trays sit flat and are secured if needed; peripheral fixing may be used in some installations.  
Final covering: Add growing media/soil on top for plant establishment.

### Product Application Summary Table

	<b>Product</b>	<b>Dry Film Thickness (min)</b>	<b>Minimum Overcoat</b>	<b>Maximum Overcoat</b>
Patching	Enviro Epoxy B-NS	Skim coat	6 hours	24 hours
Primer Coat	Enviro Prime 789	Thin, uniform coat	1 hour	5 hours
Joint Sealant	Enviro Flex FL / FC	N/A	Manufacturers Recommendations	
Membrane	Enviro HP1200	1.5mm	N/A	3 hours
Topcoat	Enviro 950TC	0.44mm	2 hours	24 hours
Drainage	Enviro H Cell / Enviro V Drain	N/A	N/A	N/A



## Basic Requirements

### Materials

- All EnviroSystems products delivered to a construction site shall be equipped with the correct original with the following information:
  - Product name.
  - Supplier information.
- All EnviroSystems materials should be inspected upon its delivery to the construction site, the material can only be used after ensuring no damage or contamination.
- When transporting and storing EnviroSystems products:
  - Stack the products separately according to product type and specifications.
  - Avoid exposure to sun and rain.
  - Keep well ventilated.
  - Control temperature, so as not to exceed 45°C.

### Application

- All applicators shall obtain sufficient and relevant training in waterproofing and the application of waterproofing membranes.
- All scaffolding and installation infrastructure shall be installed in accordance with the relevant Australian Standard.
- The preparation and maintenance of the substrate shall be undertaken observing the design and standard requirements.
- All embedded pipe fittings shall be embedded in advance in accordance with the design and standard specifications. All embedded pipe fittings should be sufficiently sealed prior to installation of the membrane.
- Application of EnviroSystems products should not occur during any form of precipitation, whilst experiencing winds greater than 40 km/h, whilst the temperature is below 5°C.
- A quality control assessment shall be completed, with full inspection and completed records indicating that the various installation procedures have been completed to a satisfactory level.
- Ensure that all installation contractors are wearing the correct Personal Protective Equipment (PPE), as per product and site requirements.
- Contractor ITP's to be adhered to and hold points signed off.
- Backfilling against retaining walls to be done not less than 24hrs after application of Enviro HP1200 and not to include the pull off adhesion test zones (as membrane in this areas requires 72hrs cure before testing).

## Quality Inspection & Assurance

### General Requirements

The approved waterproofing applicators Inspection Test Plan is to be followed and all hold points, and inspections, are to be recorded and sign off prior to subsequent works commencing.

### Pull off adhesion testing

- 2 pull off adhesion tests are required per wall.
- Pull off adhesion testing to be conducted after Enviro HP1200 is allowed to cure for a minimum of 72hrs.

### Repairing damage after pull off adhesion testing

1. Mark out section to be repair (minimum 150mm square cut out)
2. Grind back to substrate (removal of any residual araldite, primer or membrane that may be remaining after removal from adhesion testing) including lightly abrading surrounding unaffected membrane.
3. Solvent wipe of newly grinded substrate to remove remaining laitance and contaminants.
4. Apply Enviro Shield as primer (allow curing as per Product TDS) to the substrate including 150mm lap over existing unaffected membrane.
5. Spray Enviro HP1200 (as per Product TDS) to the applied primer.

## Contact Enviro systems

### NEW SOUTH WALES - HEAD OFFICE

Ground Floor, 295 Princes Highway, St Peters NSW 2044 | [info@enviro systems.com.au](mailto:info@enviro systems.com.au)

### QUEENSLAND

Unit 3, 28 Burnside Road, Yatala QLD 4207 | [info@enviro systems.com.au](mailto:info@enviro systems.com.au)

### VICTORIA

49 Wood Street, Thomastown VIC 3074 | [info@enviro systems.com.au](mailto:info@enviro systems.com.au)

### WESTERN AUSTRALIA

78 Discovery Drive, Bibra Lake WA 6163 | [perth@enviro systems.com.au](mailto:perth@enviro systems.com.au) PHONE 1300  
WATERPROOF (928 377)