

# Enviro Insulfoam

## Rigid, Medium Density Polyurethane Foam



### DESCRIPTION

Enviro Insulfoam is a two-component polyurethane HFC blown foam to produce a nominal density 32kg/m<sup>3</sup> sprayed in place polyurethane foam insulation.

### FEATURES

- Fast drying
- Easy to apply
- No CFC compounds
- Economical
- Excellent compressive strength
- High reactivity
- Solvent free
- Easy mix ratio

### TYPICAL USES

Insulation of walls, floors, decks and other areas. Enviro Insulfoam is suitable for commercial and residential applications.

- Roof insulation
- Walls and ceiling insulation
- Cool room insulation
- Filling voids in structures
- Silos and storage vessel insulation
- Pipeline insulation
- Factory and shed insulation

### PHYSICAL PROPERTIES

Density (sprayed in place)	32kg/m <sup>3</sup>
Closed Cell Content (AS2498.3)	92%
Compressive Strength (AS2498:3) parallel to the rise of foam	201kPa
Compressive Strength (AS2498:3) perpendicular to the rise of foam	112kPa
Thermal Conductivity (C518)	0.023W/mK
Mix Ratio (by volume): 1:1	1:1
Appearance Part A: Clear, Light Amber liquid	A: Light amber liquid B: Brown liquid
Specific Gravity @ 22°C	A: 1.14 B: 1.23
Brookfield Viscosity (cps) @ 22°C	A: 330 B: 250
Curing (seconds)	
Gel Time	7
Tack Free Time	10
Thermal Conductivity (C518)	0.023W/mK

### SUBSTRATE PREPARATION

Application should only be in accordance with training provided by EnviroSystems Technologies and by experienced accredited applicators. Accredited applicators must ensure the suitability of material for intended use prior to installation and any such determination is solely the responsibility of the purchaser.

The surface must be clean, dry and free from all loose particles including dust, laitance, grease, coatings, curing compounds and any other foreign matter. The substrate must be prepared by way of degreasing, grinding or captive shot blasting to provide an adequate surface profile.

For further information on substrate preparation or for project specific advice, please consult EnviroSystems.

[customerservice@envirosystems.com.au](mailto:customerservice@envirosystems.com.au)



## PRIMING

Priming of Enviro Insulfoam is dependant on substrate and weather conditions. As a general rule for priming, a light, thin dust coat of Enviro Insulfoam can be applied and allowed to cure before proceeding with normal application. Alternatively, on porous substrates Enviro Prime P2 can be applied (refer Enviro Prime P2 Product Data Sheet for directions on application).

**NOTE:** For further information on applications that may not require priming or for project specific advice, please consult EnviroSystems.

[customerservice@envirosystems.com.au](mailto:customerservice@envirosystems.com.au)

## MIXING

Typical application / processing parameters include an AP Fusion Gun and AR2020 mixing chamber with 1:1 plural component spray machinery such as a Graco E-10 or XP-2.

## APPLICATION

Application of Enviro Insulfoam should be to a maximum dry thickness of 25mm per pass. Allow Enviro Insulfoam to sufficiently cure before any subsequent pass. Dry Film thickness of each pass and final film thickness of Enviro Insulfoam can be measured by placing a spiked gauge into the cured foam until end of spike touches the substrate. Product usage varies area covered should also be noted throughout the application process as this will provide another method of determining average dry film thickness.

**NOTE:** Enviro HP1200 and HP1200PW can be applied directly over Enviro Insulfoam without the use of a primer. For optimum adhesion to Enviro Insulfoam apply subsequent Enviro membrane between 24 and 48 hours.

For further information regarding application of Enviro Insulfoam or for project specific advice please consult EnviroSystems.

[customerservice@envirosystems.com.au](mailto:customerservice@envirosystems.com.au)

## COVERAGE

The consumption of Enviro Insulfoam will depend upon substrate condition and type.

### Recommendations for Application

1 kg of Enviro Insulfoam will expand to roughly 0.027m<sup>3</sup>

## CURE

Enviro Insulfoam should be allowed to cure for 10 minutes prior to applying further passes. When the application of a waterproofing membrane such as Enviro HP1200 or HP1200PW is required, apply membrane between 1 hour and 72 hours from final application of Enviro Insulfoam.



## PACKAGING & COLOURS

Enviro Insulfoam is supplied in 43kg kits and 480kg kits.

## HANDLING PROCEDURES

The components are sensitive to humidity and should at all times be stored in sealed drums. The recommended storage temperatures are between 18-25°C, which will give a normal shelf life of 3 months. At elevated temperatures problems may arise with pressure build up within the drums. When opening these drums care must be exercised in releasing the internal pressure. It is recommended that the polyol be mixed well before use.

## HEALTH & SAFETY ADVICE

Refer to the Safety Data Sheet for full safety and handling procedures.

**NOTE:** Safety Data Sheets are available upon request by emailing [customerservice@envirosystems.com.au](mailto:customerservice@envirosystems.com.au)

## We're here to help you!

It is a good idea to keep a journal of your waterproofing job, whether big or small.

- Take pictures at all stages of your work, including preparation
- Record the quantity and description of products used with corresponding batch numbers
- Record dates and times of when you applied products, from start to finish

Please do not hesitate to contact us for any questions you may have.

EnviroSystems Technologies Pty Ltd

**Address** 295 Princes Highway, St Peters NSW 2044  
 Sydney, Australia  
**Phone** +61 2 8595 8699  
**Fax** +61 2 8595 8660  
**Email** [customerservice@envirosystems.com.au](mailto:customerservice@envirosystems.com.au)  
**Web** [www.envirosystems.com.au](http://www.envirosystems.com.au)

**DATE** April 2016



**envirosystems**  
environmentally responsible technology

### STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this publication is based on the present state of our best knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use of application and no warranty as to accuracy, reliability or completeness either expressed or implied is given other than those required by Commonwealth or State Legislation. The owner, his representative or the contractor is responsible for checking the suitability of products for their intended use. Note: Field service where provided, does not constitute supervisory responsibility. Suggestions made by EnviroSystems Technologies either verbally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not EnviroSystems Technologies are responsible for carrying out procedures appropriate to a specific application.